THE FILE COPY

AD-A216 770



HEMOSTATIC ACTIVITY OF CHITOSAN IN WOUND MANGEMENT

Technical Progress Report No. 3 for the Period July 1, 1989 to September 30, 1989

Prepared Under Contract No. N00014-89-C-0024

October, 1989

APPROVED FOR PUBLIC RELEASE DISTRIBUTION UNLIMITED

Prepared for OFFICE OF NAVAL RESEARCH Department of the Navy Arlington, VA 22217



3M Wound Management Products Laboratory

3M Center St. Paul, Minnesota 55144-1000

3M

SECURITY CLASSIFICATION OF THIS PAGE	REPORT DOCUM	MENTATION	PAGE			
1a. REPORT SECURITY CLASSIFICATION		16. RESTRICTIVE	MARKINGS	-		
Unclassified 2a. SECURITY CLASSIFICATION AUTHORITY		3. DISTRIBUTION/AVAILABILITY OF REPORT				
				<u>-</u>		
2b. DECLASSIFICATION / DOWNGRADING SCHEDU	2b. DECLASSIFICATION / DOWNGRADING SCHEDULE		Approved for Public Release Distribution Unlimited			
4. PERFORMING ORGANIZATION REPORT NUMBE	R(S)	5. MONITORING		EPORT NUMB	ER(S)	
Tachaicel Describe Deport No. 2						
Technical Progress Report No. 3	6b. OFFICE SYMBOL	7a NAME OF MO	ONITORING ORGA	NIZATION		
3M Wound Management Products (If applicable)		Office of Naval Research				
Laboratory						
6c ADDRESS (City, State, and ZIP Code)		7b. ADDRESS (Cit	=	Code)		
Building 270-4N-03 3M Center		800 N. Quir	t of the Navy			
St. Paul, MN 55144-1000		Arlington, V				
8a. NAME OF FUNDING/SPONSORING	8b. OFFICE SYMBOL	9. PROCUREMEN	T INSTRUMENT ID	ENTIFICATION	NUMBER	
ORGANIZATION	(If applicable)	Contract N	o. N00014-89-C	:_0024		
8c. ADDRESS (City, State, and ZIP Code)		10. SOURCE OF F				
,		PROGRAM	PROJECT	TASK	WORK UNIT	
		ELEMENT NO.	NO.	NO.	ACCESSION NO.	
11. TITLE (Include Security Classification)		<u> </u>	<u> </u>	<u> </u>		
Hemostatic Activity of Chitosan in Woun	d Management					
12. PERSONAL AUTHOR(S) Dr. Terry W. Lewis						
13a. TYPE OF REPORT 13b. TIME CO	VERED	14 DATE OF REPO	RT /Year Month	Dayl 15 PA	GE COUNT	
Quarterly FROM Jul	1,89 то Sept 30,8	14. DATE OF REPO 9 89 Oct 3	30	3.17	4	
16. SUPPLEMENTARY NOTATION						
17. COSATI CODES	18. SUBJECT TERMS (C	Continue on revers	e if necessary and	d identify by I	block number)	
FIELD GROUP SUB-GROUP		Collagen Chitosan G		•		
		Hemostatio				
19. ABSTRACT (Continue on reverse if necessary	and identify by block o					
	and recently by block in					
Although research has continued on the	preparation of a hen	nostatic agent in	the form of a lv	ophilized sp	onge composed of	
chitosan glutamate and collagen, resul						
identify a sponge composition which s						
Milestone 1 of the contract according to since these tasks depend on a satisfact						
methods in addition to the lyophilized sp	• • • •	•	,	سفاسا		
,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,		J 3		/ ,	F) (-	
20. DISTRIBUTION/AVAILABILITY OF ABSTRACT		21. ABSTRACT SE	CURITY CLASSIFIC	ATION		
UNCLASSIFIED/UNLIMITED A SAME AS A	PT. DTIC USERS	Unclassified	1			
228. NAME OF RESPONSIBLE INDIVIDUAL			Include Area Code	e) 22c. OFFIC	E SYMBOL	
LC McGraw		I /61	2) 733-0816	1 '		

TABLE OF CONTENTS

Sect	<u>tion</u>	<u>age</u>
EXE	CUTIVE SUMMARY	. i
1.0	INTRODUCTION	. 1
2.0 F	PROGRESS REPORT	. 1
3.0	CONCLUSIONS	2

Acces	ston For		
NTIS	GRA&I	D	
DTIC	TAB	ā	
Unam	becauser	ā	
Just!	flostion		
	ibution/	Codes	
Aval	lability (
	Avail and	/or	
Dist	Special		
A-1			
	1		

1.0 INTRODUCTION

This report covers progress during the third three months of the Office of Naval Research Contract N00014-89-C-0024. The various sections of the report are numbered and titled using the format of the original proposal.

2.0 PROGRESS REPORT

2.1 Task 2: Formulation and Optimization

During the past quarter, 3M has evaluated two compositions and two fabrication processes from Semex Medical. The lyophilized sponges were made of collagen and up to 40 weight% chitosan glutamate. The two processes yielded sponges of different bulk density. Lyophilized sponges made only from chitosan glutamate solution were also tested. The testing this quarter has been conducted in dog models. Wounds have been made in dog spleens, and the various experimental sponges have been evaluated for hemostatic activity. A dog model has also been utilized to evaluate sponges in animals in which the normal clotting cascade sequence was either hindered by platelet deactivation or inactivated by treatment with heparin. Platelet deactivation was accomplished by administration of aspirin for 7-10 days prior to surgery. Heparin was given after the spleen had been isolated.

The results obtained thus far have not met expectations. Although all compositions showed hemostatic activity in dogs without a compromised clotting system, hemostatic activity has not been observed with any of the experimental samples in the dogs treated either with aspirin or heparin. Since chitosan glutamate has been shown previously by 3M to form stable coagula in both aspirin treated and heparinized blood in vitro, it appears that the same mechanisms are not operative with current lyophilized chitosan salts tested in vivo. Based on the work thus far, it would seem that an aqueous solution of chitosan salt is necessary to achieve a stable coagulum of red blood cells. Exposure of the lyophilized forms of chitosan salts tested thus far to blood in the in vivo models must not result in appreciable solution formation of the salt and therefore hemostasis is not observed.

Milestone 1 of the proposal was for 3M to identify a final product form for the sponge product; the results of experiments conducted this quarter indicate that this milestone has not been met since all performance characteristics of the sponge product have not been met. Since solution forms of chitosan glutamate continue to show promising hemostatic activity in both in vivo and in vitro experiments, 3M will redirect the research efforts to include product formulations in which sufficient chitosan glutamate solution is delivered to the bleeding site. This concept could include simply a sterile aqueous solution which could be delivered with any sterile carrier, a sterile sponge fully soaked with aqueous chitosan glutamate, or a lyophilized chitosan glutamate/collagen sponge which readily releases the chitosan salt when exposed to water or saline.

3.0 CONCLUSIONS

Since all tasks identified in the proposal except Task 1 (Raw Material Characterization) depend on the successful completion of Milestone 1, further work on other tasks of the proposal has not been completed this quarter. Samples tested this quarter did not exhibit acceptable hemostatic activity in the compromised dog model described. Based on the experimental results obtained thus far, it appears that delivery of chitosan salt solution is critical for hemostatic activity. The research at 3M will be expanded to include this product concept.